

GLASS IONOMER SILVER REINFORCED RESTORATIVE (HUMID STABLE POWDER-LIQUID)

ISO 9917-1:2007 Glass Polyalkenoate Class 4.2b & 4.2c

DIRECTIONS FOR USE

FEATURES:

Adheres chemically to tooth substance and set amalgam. Contains fluoride ions. Low thermal conductivity and coefficient of thermal expansion is close to tooth.

Radiopaque, non-translucent. High compressive strength and hardness. Smooth polishable surface. Suitable for use with minimal cavity preparation techniques. Suitable for use with ART Technique.

INDICATIONS:

Class I and II cavities in deciduous teeth.

Repair of amalgam restored teeth when either tooth or restoration has fractured.

Class I and II cavities in selected permanent teeth.

Lining under amalgam and posterior composite restorations.

In other classes of cavity where radiopacity rather than aesthetics is a prime requirement.

As a core build-up material under crowns.

On the root surfaces for locating overdentures.

Long term temporary replacement for cusp(s),

Repairs to crown margins.

CAVITY PREPARATION:

Use minimal tooth reduction whenever possible. Calcium hydroxide liners need only be used in deep cavities. For areas of uncut surfaces, to which adhesion is required, apply Toothcleanser (25% polyacrylic acid solution) for a maximum of 30 seconds using a pledget of cotton wool, wash with water and dry with oil-free air. As freshly cut dentine or enamel is often contaminated with saliva, always apply Toothcleanser for 10 seconds immediately prior to placement. Wash with water and dry with oil-free air.

MIXING:

The recommended powder: liquid ratio is 4.5:1 mm at 22-24°C and RH 40-60%. Use a clean and dry polished glass slab or paper pad and a stainless steel 'silicate' spatula. Invert bottle to 'fluff' powder for accurate dispensing. Measure 2 scoops onto glass slab taking care not to compress powder against side of bottle with the scoop. Remove excess from scoop using a straight edge of a spatula. Dispense 1 drop of 'bubble-free' liquid onto glass slab. Incorporate half the powder into the liquid and mix for 10-15 seconds, then add the remaining powder and spatulate to a stiff uniform putty-like consistency. Total mixing time 30 seconds. **DO NOT ADD POWDER IN SMALL INCREMENTS.**

WORKING TIME: A minimum of 1 minute 45 seconds from start of mix at 22-24°C

CLINICAL SETTING TIME: A maximum of 3½ minutes from end of mix.

PLACEMENT:

Condense the material into cavity using normal instruments. To avoid material adhering to instruments, dip the clean instrument into methylated spirit. When using stainless steel matrix bands around class II cavities, coat lightly with petroleum jelly. The use of coated soft aluminium in the form of either interproximal strips or preformed cervical matrices is recommended; neither require lubrication. Avoid contamination with saliva or water during placement. Immediately after removal of matrix apply a thin layer of light-cured resin with a suitable brush and cure, using a surgery light at 470nm for 10 seconds. Alternatively a varnish can be used. Re-apply glaze or varnish following any subsequent adjustment to ensure maximum protection.

FINISHING:

The surface may be carved and contoured using the conventional instruments that are employed with amalgam. This must **NOT** go beyond the end of the working time when the cement begins to harden. It is hard enough to withstand the use of rotary instruments after 7 minutes.

Trimming and contouring. Removal of appreciable quantities of the set cement is best accomplished with sandpaper discs, stainless steel burs, or green stones in a low speed handpiece. Petroleum jelly should be applied to prevent frictional heating and consequent desiccation.

Finishing. Final adjustment of the surface is best carried out using white Stones or alumina discs.

Polishing/burnishing. As with amalgam and glass ionomer, a better polish is obtained at a subsequent visit. The best results are obtained using Shofu Greenies or Super-Snap green discs. At whatever stage the finishing process is completed, it is recommended to coat the surface with glaze or varnish.

STORAGE:

Store both powder and liquid in a cool dry place. Both powder and liquid can withstand warm humid conditions.

WARNING:

Avoid contact of liquid and powder with eyes. In the event of contact, rinse with copious quantities of water and seek medical assistance.

BATCH CODE:



The batch code gives an open date of manufacture in month, year, day format with a numerical suffix to uniquely identify the batch of material. Please quote this batch number in all correspondence.



The expiry date is shown in year, month format. Do not use the product after this date.

ISO 9917 NET SETTING TIME: A maximum of 3 minutes from end of mix at 36-38°C

TESTING:

For test purposes the powder: liquid ratio is 0.90g to 0.20g at 22-24°C & 40-60% RH.

SPECIALLY FORMULATED FOR USE IN DENTISTRY

REF:	232XPL	10g Powder / 5ml Liquid
	232XPLJ	30g Powder / 10ml Liquid



Advanced Healthcare Ltd., Tonbridge, Kent, TN11 8JU, UK
Tel: +44 1892 870500 Fax: +44 1892 870482

Advanced Healthcare Ltd operate a policy of continuous monitoring and improvement of our products. If you have any comments about this product, please contact us at the above address stating the batch number shown on the packaging.

Caution: U.S. Federal Law restricts this device to sale by or on the order of a dental professional.