



FLEXURAL STRENGTH MPa

41.7



- ✓ Good adhesion
- ✓ Needs no primer
- ✓ Mixes easily
- ✓ Good handling
- ✓ Radiopaque



AHLute + Resin Modified Glass Ionomer Luting Cement

This self-curing, resin modified glass ionomer luting cement is ideal for luting metal crowns, bridges, inlays, onlays and “all ceramic” restorations.

Indications

Cementing of all metal crowns, bridges, inlays and onlays
 Cementing of metal orthodontic brackets to tooth structure

Features

Good adhesion
 Needs no primer
 Mixes easily
 Good handling
 Radiopaque

Advantages

Secure long lasting restorations
 Patient and user friendly
 Time saving, economical
 Easy to use
 Shows on X-rays

Bottle delivery contains a mixing pad and scoop.

Available in	Code
Powder/Liquid 15gm/7ml	AH0500

Property	ISO9917-2:2017	Typical Properties
Working Time	-	2 mins 40 secs
Net Setting Time	1 min 30 secs – 8 mins	4 mins
Flexural Strength	10MPa	41.7MPa
Film Thickness	25µm Maximum	14µm

Your global partner

Delivering quality for more than 30 years

Advanced Healthcare Ltd.

Units 2-4 Leavers Estate, Chiddingstone Causeway, Tonbridge, Kent TN11 8JU UK
 Tel: +44(0)1892 870500 Fax: +44(0)1892 870482 Email: sales@ahl.uk.com

www.ahl.uk.com

Authorised distributor