



AHL

Advanced Healthcare Ltd.

FLEXURAL STRENGTH MPA

55



- ✓ Dual curing mechanism
- ✓ High compressive strength
- ✓ High flexural strength
- ✓ Good shear bond strength
- ✓ Radiopaque



50 x Single use capsules

A2 A3

AHfil LC Light Curing Resin Modified Restorative Capsules

AHfil glass ionomer filling materials are manufactured using translucent alumina-silicate glass that offers good aesthetics without compromising on strength and wear resistance.

The material features both chemical and light curing mechanisms to ensure the best mix of early strength and command setting. Offering both good compressive and flexural strengths to provide durable restorations. High shear bond strength to both dentine and enamel ensures good adhesion to the natural tooth structure. Available in two popular Vita® shades to enable accurate matching to the natural tooth structure.

Indications

Deciduous cavity restoration
Class V and III restorations
Core Build up

Features

Dual curing mechanism
High compressive strength
High flexural strength
Good shear bond strength
VITA® shades
Radiopaque

Advantages

Provides strength and control
Offers good compression resistance
Gives good flexibility in the key areas
Great adhesion to tooth structure
Accurate colour matching
Shows on X-rays
Good handling characteristics

Available in	Code
A2	AH0310
A3	AH0311

Property	ISO9917-2:2010 Class 4.2c	Typical Properties
Flexural Strength	25MPa	55MPa
Compressive Strength	—	221MPa
Shear Bond Str (Dentine)	—	11.7MPa
Shear Bond Str (Enamel)	—	12.1MPa
Radiopacity (mm)	1.0	2.5

Your global partner
Delivering quality for more than 30 years

Advanced Healthcare Ltd.

Units 2-4 Leavers Estate, Chiddingstone Causeway, Tonbridge, Kent TN11 8JU UK

Tel: +44(0)1892 870500 Fax: +44(0)1892 870482 Email: sales@ahl.uk.com

www.ahl.uk.com

Authorised distributor

© 2025 Advanced Healthcare Ltd. E&OE.