



COMPRESSIVE STRENGTH MPa

250



- Radiopaque
- Dual-cure
- Sel-levelling
- Flexural strength

RAY

reliaFlow Bulk

reliaFlow Bulk is an advanced flowable composite predominately designed as a base under class I & II restorations.

A bulk filling composite with ideal shade opacity, low shrinkage and full polymerisation at 4mm depth of cure. The self-levelling characteristics produce good cavity adaptation. Suitable for use with both Halogen and LED curing lights.

Indications

Base in class I & II direct restorations. Liner under direct restorative materials.
Restorations of small posterior cavities (including occlusal restorations).

Features

Can be placed in 4mm layers Self-levelling action High filler content High level of radiopacity

Advantages

High depth of cure Easy adaptation Reduced polymerisation shrinkage Shows on X-rays

U		D

Syringe 2gm

Available in	Code	Available in	Code
Universal	AH0920	Dentine	AH0921

Property	ISO4049:2019	Typical Properties
Flexural Strength	80MPa	115 MPa
Depth of Cure (mm)	1mm min	4mm
Radiopacity Al/ mm	1.0mm	2.5mm
Compressive Strength	-	250MPa
Vickers Hardness	-	42

Your global partner

Delivering quality for more than 30 years

Advanced Healthcare Ltd.

Units 2-4 Leavers Estate, Chiddingstone Causeway, Tonbridge, Kent TN11 8JU UK Tel: +44(0)1892 870500 Fax: +44(0)1892 870482 Email: sales@ahl.uk.com

www.ahl.uk.com © 2025 Advanced Healthcare Ltd. E&OE.

Authorised distributor