





Glass Ionomer Aesthetic Restorative (Powder/Liquid)

ISO 9917-1 Glass Polyalkenoate

DIRECTIONS FOR USE

FEATURES:

Adheres chemically to enamel, dentine and cementum. Coefficient of thermal expansion close Suitable for use with minimal cavity preparation techniques. A fast setting Glass lonomer with excellent translucency and optimum aesthetics. Contains fluoride.

INTENDED PURPOSE:

Restoration of lost tooth structure

INTENDED PATIENT POPULATION: From child to geriatrics

INTENDED USER:

This product has been formulated for use in dentistry and is intended for use by dental professionals only.

CLINICAL BENEFIT:

To restore the function of the teeth and help maintain the integrity of the remaining tooth structure

INDICATIONS FOR USE:

- Class V cavities
- Class III cavities
- Class I and II cavities in deciduous teeth.
- Pits and fissures

CONTRA-INDICATIONS:

Pulp capping.

CONTENTS OF PACK:

Powder 15g, Liquid 7ml, measuring scoop, instructions for use

PRECAUTIONS AND WARNINGS:

- Do not expose patients or users known to be allergic to this type of material.
 Avoid contact of liquid and powder with oral mucosa, eyes, and skin.
- In case of contact, wash thoroughly with water and obtain medical advice.
- •DO NOT use product for any purpose other than indicated.

PROCEDURE

(1) CAVITY PREPARATION:

Use minimal tooth reduction whenever possible. Calcium hydroxide liners need only to be used in deep cavities. For areas of uncut surfaces, to which adhesion is required, apply Toothcleanser (25% Polyacrylic acid solution) for a maximum of 30 seconds using a pledget of cotton wool. Wash with water and dry with oil-free air. In areas, which are heavily coated with plaque or tartar, Prophylaxis with oil free Prophypaste prior to tooth cleansing is required. If freshly cut dentine or enamel is contaminated with saliva, apply Toothcleanser for 10 seconds only before washing with water and drying with oil free air.

(2) MIXING:

The recommended powder-liquid ratio is 4.5:1 mm at 22-24°C and RH 40-60%. Use a clean and dry polished glass slab or paper pad and a stainless steel spatula. Invert bottle to 'fluff powder for accurate dispensing. Measure ONE scoop of powder onto glass slab taking care not to compress powder against side of bottle with the scoop. Remove excess powder from the scoop using the straight edge of the semi-circular insert. Dispense ONE 'bubble-free' drop of liquid onto glass slab. Incorporate half the powder into the liquid and mix for 10-15 seconds, then add the remaining powder and spatulate to a uniform putty-like consistency.

DO NOT ADD POWDER IN SMALL INCREMENTS.

Total mixing time: 30 seconds Working time: 2 minutes from start of mix at 23°C Setting time: 3 minutes from placement in the oral cavity

For test purposes, the ratio of powder 0.90g to liquid 0.20g tested at 23 \pm 1°C & RH 50 \pm 10%. ISO 9917-1 net setting time: 2 to 6 minutes from start of mix at 36-38°C & RH 90-100%.

(3) PLACEMENT:

Place into cavity using normal instruments. To avoid material adhering to instruments, dip the clean instrument into the powder or methylated spirit. When using stainless steel matrices, coat lightly with petroleum jelly. The use of coated soft aluminium in the form of either interproximal or cervical matrices is recommended, these do not require lubrication. Avoid contamination of filling with saliva or water during placement. Immediately after removal of matrix, apply a thin layer of light-cured resin with a suitable brush and cure for 10 seconds. Alternatively, a varnish may be used. Re-apply glaze or varnish following any subsequent adjustment to ensure optimum aesthetics.

Best results are obtained by polishing with abrasive discs or stones at a subsequent visit using water spray lubrication. At 7 minutes after placement, the material is hard enough to finish using abrasive discs and stones, but petroleum jelly must be used as a lubricant to prevent excess heat and desiccation of cement. For optimum polished surface white stones and alumina discs should be used. After finishing, it is recommended to coat the surface with glaze or varnish for protection from moisture.



Store in a cool, dry place (5-25°C). Always replace cap immediately after use.

EXPIRY:



The expiry date is shown in year, month format. Do not use the product after this date

DISPOSAL:

Dispose of the contents and containers in accordance with relevant local and national requirements

POSSIBLE SIDE EFFECTS / RESIDUAL RISKS:

• This product contains substances that may cause and allergic reaction.

BATCH CODE:



The batch code gives an open date of manufacture in month, year, day format with a numerical suffix to uniquely identify the batch of material. Please quote this batch number in all correspondence.

REF

AH0001 15g Powder Shade A1 / 7ml Liquid AH0002 15g Powder Shade A2 / 7ml Liquid 15g Powder Shade A3 / 7ml Liquid AH0003 15g Powder Shade A3.5 / 7ml Liquid 15g Powder Shade B2 / 7ml Liquid 15g Powder Shade B4 / 7ml Liquid AH0004 AH0005 AH0006 AH0007 15g Powder Shade C3 / 7ml Liquid AH0008 15g Powder Shade CB / 7ml Liquid





COMPOSITION:

Composition	% by weight
Glass powder	60 – 80
Water	10 - 25
Polyacrylic Acid	10 – 20
Tartaric Acid	0 – 5

AHL operate a policy of continuing surveillance & monitoring of our products. If you experience any incidents relating to the use of this product, please immediately contact us at the below address stating the batch number shown on the packaging. If you experience any serious incident relating to the use of this product, please immediately contact AHL at the below address and the competent authority of the territory you are in.

A summary of safety & clinical performance (SSCP) is available via the EUDAMED database. https://ec.europa.eu/tools/eudamed

Caution: U.S. Federal Law restricts this device to sale by or on the order of a dental professional

Advanced Healthcare Ltd., Tonbridge, Kent, TN11 8JU, UK Tel: +44 1892 870500 Email:sales@ahl.uk.com

EC REP Advena Ltd. Tower Business Centre, 2nd Flr., Tower Street, Swatar, BKR 4013

2025-02 AP6855/2